

Product Bulletin

Concept[®] 105 HIGH GLOSS OVERLAMINATING FILM

Concept[®] High Gloss Overlaminating Film is a pressure sensitive 2.0 mil polyester film with the optically clear 204-4100 permanent acrylic adhesive on a 1.5 mil polyester film liner. This polyester film offers protection from abrasion, moisture and other environmental exposures. It is laminated by the cold laminating process without the addition of heat.

Applications	High Gloss overlaminating polyester film is designed to protect digital image prints and screen-printed images for exhibit and display graphics. May also be used to protect printed signage both interior and exterior. This film can be used to enhance image clarity, contrast, and brilliance.
Thickness	Film 2.0 mils. Adhesive .8 to 1.1 mils. Liner 1.5 mils. (Thickness variance +/- 10%)
Dimensional Stability	Good.
Temperature Ranges	Minimum application temperature +40° F. Service temperature range -40°F to +200°F.
Adhesion	To stainless steel 48 oz/in. When tested according to PSTC-1 with 24 hr. dwell at 70°F and 50% relative humidity. Typical values. Individual values may vary. Test thoroughly before production.
Exterior Durability	The polyester film and adhesive have good resistance to discoloration caused by exterior exposure. Under normal exterior exposure conditions Concept 105 could protect the under-laying graphics for up to 2-years from fading caused by typical exterior exposure conditions.
Light Transmission	Approximately 84% @ 550nms.
Gloss 60 ° Gardner	100+.
Storage Stability	1-year shelf life when stored at 70°F and 50% relative humidity.
Product Series	Concept [®] #105



***Manufacturer of Pressure Sensitive Films,
Traffic Graffice Floor Advertising Films,
Custom Coatings and Printing Inks.***

309 S. Union • P.O. Box 158 • Sparta, Michigan 49345 • (616) 887-7387 • (800)253-3664 • FAX (616)887-0537
Web Site: www.generalformulations.com • e-mail: gfiinfo@generalformulations.com

We believe the information on this product to be accurate. However, since we cannot anticipate or control the conditions under which this information or our products may be used, we cannot guarantee results obtained through their use. Tests of our products should be made by users to determine the suitability of these products for a specific purpose. The products are sold without warranty, either express or implied. The purchaser should refer to General Formulations, Inc's Price List for Terms and Conditions or Sale, Including Disclaimer of Warranties and Limitation of Liability.