

# Product Bulletin

## OVERLAMINATING POLYESTER

### PERMANENT ADHESIVE

A 1.0 or 2.0 mil clear polyester film coated with 200-4990 permanent acrylic pressure sensitive adhesive on either a 2.0 mil polypropylene or 53# paper overlaminate liner.

<b>Application</b>	Designed for general purpose overlaminate film for decals or nameplates for protecting the underlying graphics.		
<b>Thickness</b>	Film	1.0 mil or 2.0 mils.	
	Adhesive	0.8 to 1.0 mils.	
	Liner	Polypropylene	2.0 mils.
	Paper	3.0 mils.	
	(Thickness variation +/- 10%)		
<b>Dimensional Stability</b>	Good.		
<b>Temperature Ranges</b>	Minimum application temperature is +50°F. Service temperature range is -40°F to +250°F.		
<b>Adhesion</b>	To stainless steel - 40 oz./ in. PSTC-1 with 24-hour dwell at 70°F and 50% relative humidity. Typical values. Individual values may vary.		
<b>Exterior Durability</b>	Overlaminate Polyester AP has very good resistance to discoloration caused by UV light.		
<b>Product Variations</b>	Polyester is available in either a matte or gloss finish. A 53# paper overlaminate liner is also available.		
<b>Water Resistance</b>	Limited immersion resistance. Test specific application. Wet application may produce an adhesive fog. This condition will usually clear within 48 hours at normal temperature and humidity.		
<b>Humidity Resistance</b>	Good. High humidity may induce an adhesive fog. This condition will usually clear within 48 hours at normal temperature and humidity.		
<b>Storage Stability</b>	One year shelf life when stored at 70°F and 50% relative humidity.		
<b>Product Codes</b>		<u>Polypropylene Liner</u>	<u>Paper Liner</u>
	1.0 mil gloss	C1-OL-AP/CLR	C1-OL-AP/53#
	1.0 mil matte	M1-OL-AP/CLR	N/A
	2.0 mil gloss	C2-OL-AP/CLR	N/A



**Manufacturer of Pressure Sensitive Films,  
Traffic Graffiti Floor Advertising Films,  
Custom Coatings and Printing Inks.**

309 S. Union • P.O. Box 158 • Sparta, Michigan 49345 • (616) 887-7387 • (800)253-3664 • FAX (616)887-0537  
Web Site: [www.generalformulations.com](http://www.generalformulations.com) • e-mail: [gfiinfo@generalformulations.com](mailto:gfiinfo@generalformulations.com)

We believe the information on this product to be accurate. However, since we cannot anticipate or control the conditions under which this information or our products may be used, we cannot guarantee results obtained through their use. Tests of our products should be made by users to determine the suitability of these products for a specific purpose. The products are sold without warranty, either express or implied. The purchaser should refer to General Formulations, Inc's Price List for Terms and Conditions or Sale, Including Disclaimer of Warranties and Limitation of Liability.