

TECHNICAL DATA SHEET

GF 223AE

6.0 MIL MATTE WHITE SEMI-RIGID VINYL
CLEAR LOW-TACK REMOVABLE ADHESIVE
WITH AIR EGRESS

GF 223AE is a 6.0 mil matte white semi-rigid vinyl with a removable acrylic pressure sensitive adhesive on a 90# Air Egress liner. This vinyl is designed to accept a variety of solvent-based, UV curable and latex inks common to wide format digital printing systems. GF 223AE is a removable decal film designed for ease of application of temporary interior or exterior signage (up to 3 years), decals, and point-of-purchase displays. Semi-Rigid films are easy to handle due to their rigidity and thus can be applied quickly.

PRODUCT NAME	223AE
FILM	
Film Type	White Polymeric Vinyl
Film Thickness (mils/μm)	6.0 / 152 (+/- 10%)
Film Weight (gsm)	215
Gloss (60°)	≤ 20
Opacity (%)	99
Tensile Strength (lbs/in ²)	MD ≥ 3300 / CD ≥ 3200
Elongation (%)	MD ≥ 100 / CD ≥ 125
Dimensional Stability (FTM 14)	MD ≤ 0.50 mm / CD ≤ 0.20 mm
ADHESIVE	
Adhesive Type	Emulsion Acrylic
Adhesive Thickness (mils/μm)	0.8-1.0 / 20-25
Adhesive Color	Clear
Peel Strength on Stainless Steel (lbs/in) / (N/25mm) 15 min	0.08-0.30 / 0.3-1.3
Peel Strength on Stainless Steel (lbs/in) / (N/25mm) 24 hrs	0.08-0.30 / 0.3-1.3
Peel Strength on Glass (lbs/in) / (N/25mm) 15 min	0.04-0.30 / 0.2-1.3
Peel Strength on Glass (lbs/in) / (N/25mm) 24 hrs	0.04-0.30 / 0.2-1.3
LINER	
Liner Weight (#/gsm)	90 / 145
Liner Type	White 2-Sided PE-Coated Kraft Air Egress
Liner Thickness (mils/μm)	7.0 / 180
Release Force @ 300" / min (g/2")	70-130
PERFORMANCE GUIDANCE	
Application Temperature	≥ +40 °F
Service Temperature	-40 °F to 180 °F
Shelf Life	1 year
Storage Temp / Rel. Humidity	70 °F / 50%
Outdoor Durability	Up to 3 years
Removability	Up to 1 year

**All values provided are typical averages intended for guidance only and should not be interpreted as product specifications or warranties.*

GF 223AE | SEPTEMBER 2026

TECHNICAL DATA SHEET

GF 223AE - 6.0 MIL MATTE WHITE SEMI-RIGID VINYL CLEAR LOW-TACK REMOVABLE ADHESIVE WITH AIR EGRESS

PRODUCT SNAPSHOT	APPLICATIONS	INK TYPE
APPLICATION ☐ WET APPLY ☒ DRY APPLY ☐ LAMINATING ☐ MOUNTING ☒ DIE CUTTABLE ☐ HOT STAMP ☐ THERMAL DIE ☒ FLATBED CUTTABLE	☒ POP/RETAIL ☐ WALL ☐ WRAP ☒ WINDOW ☐ FLOOR ☐ TRANSLUCENT ☐ FLEET ☒ GENERAL SIGNAGE ☒ INDOOR ☒ OUTDOOR	☒ SOLVENT ☒ ECO-SOLVENT ☒ LATEX ☒ UV CURABLE ☒ SCREEN ☒ OFFSET (UV CURABLE) ☐ OFFSET (CONVENTIONAL)
SUBSTRATES ☒ OEM PAINTED METAL ☒ PAINTED ALUMINUM ☒ STAINLESS STEEL ☒ GLASS		

FAQS

Can I use GF 223AE on other surfaces?	GF 223AE works great with flat, smooth surfaces. It is a great solution for temporary store front applications requiring bond to windows.
What if I leave GF 223AE on past it's optimal removability time frame?	GF 223AE will always be removable, but you may have some percentage of adhesive transfer when left on past the 1 year clean removal timeline.
Can this product be used on Elevators?	These types of doors may have a clear coat or other type of protection. This product is not designed for coated/sealed/treated stainless steel, brass or bronze surfaces. It is best to contact the facility manager and determine the best product for this application.