

Product Bulletin

FLEXIBLE VINYL PERMANENT ADHESIVE

This general purpose decal stock is a 3.4 or 8.0 mil (white only) matte flexible calendared vinyl film coated with 200-4990 permanent acrylic pressure sensitive adhesive on a 90# layflat liner. These films are designed to accept a variety of UV curable and solvent-based screen inks and could be topcoated for use with flexographic, offset and letterpress inks but must be tested prior to use.

Applications	These products are designed for signage, decals, nameplates, die-cut letters and point-of-purchase displays.	
Thickness	Film	3.4 mils or 8.0 mils.
	Adhesive	.8 to 1.0 mil.
	Liner	6.7 mils.
	(Thickness variance +/- 10%)	
Dimensional Stability	Good.	
Temperature Ranges	Minimum application temperature is +40°F. Service temperature is -40°F to +180°F.	
Expected Exterior Exposure	Up to 3 years.	
Adhesion	To stainless steel	48 oz/in.
	PSTC-101 Method A with 24 hr. dwell at 70°F and 50% relative humidity.	
	Typical value. Individual values may vary.	
	Test thoroughly before production.	
Water Resistance	Limited immersion resistance. Test specific application.	
Humidity Resistance	Good.	
Gasoline Resistance	No edge lift – 15 minute immersion.	
Solvent Resistance	Good	
Storage Stability	2 year shelf life when stored at 70°F and 50% relative humidity.	
Product Codes and Colors Available	VFW-NTC-AP/90#	(White, non-topcoated)
	VFW-TC-AP/90#	(White, topcoated)
	VFW8-NTC-AP/90#	(White, non-topcoated)
	VFY-NTC-AP/90#	(Yellow, non-topcoated)
	VFDY-NTC-AP/90#	(Deep Yellow, non-topcoated)
	VFB-NTC-AP/90#	(Black, non-topcoated)



**Manufacturer of Pressure Sensitive Films,
Traffic Graffice Floor Advertising Films,
Custom Coatings and Printing Inks.**

309 S. Union • P.O. Box 158 • Sparta, Michigan 49345 • (616) 887-7387 • (800)253-3664 • FAX (616)887-0537
Web Site: www.generalformulations.com • e-mail: gfiinfo@generalformulations.com

We believe the information on this product to be accurate. However, since we cannot anticipate or control the conditions under which this information or our products may be used, we cannot guarantee results obtained through their use. Tests of our products should be made by users to determine the suitability of these products for a specific purpose. The products are sold without warranty, either express or implied. The purchaser should refer to General Formulations, Inc's Price List for Terms and Conditions or Sale, Including Disclaimer of Warranties and Limitation of Liability.