

# Product Bulletin

## ULTRA TACK SEMI RIGID WHITE VINYL HIGH TACK PERMANENT ADHESIVE

A 3.4-mil matte white-calendered vinyl film coated with 200-4998 high tack permanent acrylic pressure sensitive adhesive on a 90# layflat liner. This vinyl film is designed to accept a variety of UV curable and solvent-based screen inks. Additionally this film may also offer adhesion to UV flexographic, UV offset, letterpress inks, and some thermal ribbon inks but must be tested prior to use. The 90# layflat liner offers good dimensional stability over a range of environmental conditions resulting in excellent sheet printing.

**Applications** This product is designed for permanent decals and nameplates requiring adhesion to a variety of substrates ranging from clean metal, painted metal, glass, styrene and low surface energy plastics such as polypropylene and polyethylene. May also be applicable to certain powder coated metal finishes. Must be tested prior to use.

**Thickness**

Film	3.4 mils.
Adhesive	0.8 to 1.1 mils.
Liner	6.7 mils.

(Thickness variance +/- 10%)

**Dimensional Stability** Good.

**Temperature Ranges** Minimum application temperature is 40°F.  
Service temperature is -40°F to +200°F.

**Expected Exterior Exposure** Up to five years.

**Adhesion**

To Stainless Steel	80 oz/in.
Glass	80 oz/in.
Polypropylene	60 oz/in.
Polyethylene	40 oz/in.

PSTC-1 with 24-hour dwell at 70°F and 50% relative humidity. Typical values. Individual values may vary. Test thoroughly before production.

**Water Resistance** Excellent

**Humidity Resistance** Excellent

**Storage Stability** 1-year shelf life when stored at 70° F and 50% relative humidity.

**Product Code** VSR-NTC-HTP/90#



**Manufacturer of Pressure Sensitive Films,  
Traffic Graffic Floor Advertising Films,  
Custom Coatings and Printing Inks.**

309 S. Union • P.O. Box 158 • Sparta, Michigan 49345 • (616) 887-7387 • (800)253-3664 • FAX (616)887-0537  
Web Site: [www.generalformulations.com](http://www.generalformulations.com) • e-mail: [gfiinfo@generalformulations.com](mailto:gfiinfo@generalformulations.com)

We believe the information on this product to be accurate. However, since we cannot anticipate or control the conditions under which this information or our products may be used, we cannot guarantee results obtained through their use. Tests of our products should be made by users to determine the suitability of these products for a specific purpose. The products are sold without warranty, either express or implied. The purchaser should refer to General Formulations, Inc's Price List for Terms and Conditions or Sale, Including Disclaimer of Warranties and Limitation of Liability.